

Product Characteristics

Part Number: BIZHSTW5CL/4FT

HEATSHRINK 5MM CLEAR 4FT



Description:

Thin wall 2/1 heat-shrink tubing without adhesive.

Application(s):

For general and specific applications in the following areas: electrical insulation, marking and identification, protection (mechanical against corrosion), management and maintenance of wires.

Technical details:

Thin wall, 2/1 shrinkage in length 1.2 meter.

Heat-shrink tubing in flexible flame retardant polyolefin (except clear).

Working temperature: -45 °C to +125 °C (clear is -45 °C to +105 °C).

Shrink temperature: 120 °C (clear is 105 °C).

Dielectric strength (IEC 243): 15 kV/mm.

Tensile strength: 10.4 Mpa.

Rate voltage: 600 V.

Self-extinguishing in accordance with UL224 (except clear).

| Attribute Name | Attribute Value |
|--------------------|-----------------|
| Colour | Transparent |
| AWG wall thickness | Thin-walled |
| With inner glue | No |
| Length | 4 ft |
| Shrink rate | 2:1 |

| Classifications | |
|-----------------|----------|
| ETIM | EC000217 |
| UNSPSC | 40183006 |

Create Date: 01/11/2019

Disclaimer

For use on datasheets that are created by Rexel

The information in this document is intended to provide a brief summary of our knowledge of this product. It has been compiled from sources we believed at the time of compilation to be reliable and accurate. It is not meant to be an exhaustive and complete document about the product. Rexel does not warrant that it is accurate, complete or up to date.

Each user of this information needs to verify (including by its own risk analysis, evaluation and testing) the product's characteristics and features in light of its particular intended use for the product. Each user should, before purchasing this product and before use, obtain the latest relevant information from the manufacturer, details of which can be provided by the Rexel Australia group.

The Rexel Australia group excludes all warranties or guarantees implied by law, and all liability for any error, inaccuracy, loss or damage resulting from the use of this information. No rights to reproduce this document are granted by the publication of this document. This publication may be changed at any time.